

Homopolymer

Description:	"Jampilen HP502P" is a homopolymer with good flow properties and medium molecular weight distribution intended for fiber extrusion applications. "Jampilen HP502P" has a high fluidity and best suits for the production of staple fibers, bulk continuous filaments (BCF) and continuous filaments (CF). It contains a general purpose formulation of additives with no antigasfading additivation.
Processing Method:	Fiber Extrusion
Features: Typical Applications:	Good Flow Properties Consistent processability Medium Molecular Weight Distribution Homopolymer BCF and CF Yarns Staple fibers

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	17	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1550	MPa	ASTM D790
Tensile Strength at Yield	33	MPa	ASTM D638
Tensile Elongation at Yield	12	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	30	J/m	ASTM D256
Rockwell Hardness	103	R Scale	ASTM D785
Thermal			
Vicat softening point (10N)	154	°C	ASTM D1525
H.D.T. (0.46 Mpa)	95	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012

4th Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran. Tel: +9821-84286, Fax: +9821-88879811 Email: info@jppc.ir www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.