



## **Description:**

## P-SF-060 Homopolymer

**"Polynar P-SF-060"** is a polypropylene homo-polymer with good flow properties and practicularly suitable for the extrusion of film yarn, monofilament, cast film and sheet.

"combines outstanding processability with good mechanical properties.

film yarn of **Polynar P-SF-060**, is ued for baler twines, packaging twines and ropes.

Polynar P-SF-060 is well suited for the production of monofilament usd for instance in brush and broom filling and technical applications.

**"Polynar P-SF-060"** is suitable for the production in film yarn industry for bags & heavy duty jumbo bag.

**Processing Method:** "Polynar P-SF-060" is suitable for food contact.

**Features:** Extrusion (film yarn, monofilament) -sheet- cast film

good processibility

good mechanical properties

homopolymer

**Typical Applications:** 

production in film yarn industry for bags & heavy duty jumbo bag

Baler twines, packaging twines and ropes.

Thin sheet for stationery folders.

Sheet for thermoforming

Brush and broom filling and technical applications.

parts for automotive industry, toys, and the garden furniture

ISO 9001 OHSAS 18001

ISO 14001





TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	6.0	g/10min	ASTM D1238
Density	0.90	g/cm <sup>3</sup>	ASTM D1505
Mechanical			
Flexural Modulus	1500	MPa	ASTM D790
Tensile Strength at Yield	35	MPa	ASTM D638
Tensile Elongation at Yield	12	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	30	J/m	ASTM D256
Thermal			
Vicat softening point (10N)	154	° C	ASTM D1525
H.D.T. (0.46 Mpa)	94	°C	ASTM D648

Head Ofice: NO:10 , Danially Alley , Andarzgoo Boulevard, TEHRAN-IRAN

TEL:(+9821)22212087 FAX:(+9821)22201946

Factory: West of TABRIZ Petrochemical Complex – TABRIZ-IRAN

TEL:(+98411)4201000 FAX:(+98411)4201001 www.polynar.com Email:info@polynar.ir